

# Boltaron® 9815 with a Pressed Texture

CUSTOM TEXTURED FAR 65/65 SHEET

9 0 0 0  
S E R I E S

## PERFORMANCE DETAILS

### FAR RATINGS

FAR 25.853(a)(i)	(Flammability) Pass
FAR 25.853(a)(ii)	(Flammability) Pass
FAR 25.853(d)(Part IV)	(OSU Heat Release) (Peak - HRR, kW/m <65) (2 Min - HRR, kW/m <sup>2</sup> <65)
FAR 25.853(d)(Part V)	(NBS Smoke) (Ds Max <200)

### PROPERTIES

<b>Specific Gravity</b> (ASTM D792)	1.490
<b>Tensile Strength</b> (ASTM D638)	5,500 psi (38 MPa)
<b>Flexural Strength</b> (ASTM D790)	8,700 psi (60 MPa)
<b>Flexural Modulus</b> (ASTM D790)	410,000 psi (2,827 MPa)
<b>Izod Impact (notched) @ 73°F (23°C)</b> (ASTM D256)	5.0 ft-lb/in (265 J/m)
<b>Hardness Rockwell</b> (ASTM D785)	107
<b>Heat Deflection Annealed</b> (ASTM D648)	170 °F @ 264 psi (77 °C @ 1.8 MPa)
<b>Thermal Expansion</b> (ASTM D696)	1.67 x 10 <sup>-5</sup> /°F (3 x 10 <sup>-5</sup> /°C)

\* Independent lab tests.

### QUALITY CHARACTERISTICS

- Outstanding impact resistance
- Unique texture options, including carbon fiber, leather, and many more
- Uniform high quality appearance
- Wall thickness integrity in deep draw forming
- Lot-to-lot texture and color consistency

### USES

Instrument panel housings, class dividers, bulkhead laminates, galley and lavatory components, bull noses, gap covers, moldings, sidewall and kick panels, window reveals, seat parts, backs, arm rests, tray tables, passenger service units (PSUs), light housings, video monitor shrouds, life vest shrouds, air ducts

### SHEET SIZES

<b>Lengths</b>	99 or 122 in (2,514 or 3,099 mm)
<b>Widths (varies for each texture)</b>	up to 50 in (1,270 mm)
<b>Gauges</b>	from 0.040 to 0.250 in (1.02 to 6.35 mm)
<b>Custom</b>	Blank sizes, gauges on request

### THERMOFORMING GUIDELINES

<b>Mold Shrinkage</b>	0.5 - 0.7%
<b>Forming Temperature</b>	335 - 370 °F (168 - 188 °C)
<b>Typical Heater Settings (Top)</b>	30 - 50%
<b>Typical Heater Settings (Bottom)</b>	50 - 70%
<b>Drying</b>	Not required

9815P  
PRESSED

### DESIGN OPTIONS

<b>Colors</b>	Unlimited
<b>Textures</b>	Wide Range Available
<b>Effects</b>	Metallic or True Pearl
<b>Images</b>	Impress Prints
<b>Minimum</b>	500 lb

DISCLAIMER AND LIMITATION OF WARRANTY: All information contained herein is believed by SIMONA BOLTARON Inc. to be reliable. Typical properties are based on laboratory tests conducted on material samples in accordance with standard test methodology. SIMONA BOLTARON Inc. makes no express or implied warranty that its products will perform in accordance with the data in all conditions and circumstances. To determine suitability for use, users must test applications under actual operating conditions. As a result, ALL EXPRESS OR IMPLIED WARRANTIES IN CONNECTION WITH SIMONA BOLTARON Inc. PRODUCTS INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY DISCLAIMED.

MS 06/27

**SIMONA**  
**boltaron**

[www.boltaron.com](http://www.boltaron.com) | +1 800 342 7444

RELIABILITY MEETS INNOVATION