

Boltaron® 4300

CLEAR TYPE II PVC

CORROSION
RESISTANT

CHARACTERISTICS

- High impact resistance
- Corrosion resistant
- Suitable for thermoforming
- Conforms to ASTM D1784
- Clear, smooth, polished surface on both sides

USES

- Equipment windows
- Machined parts
- Thermoformed parts

PERFORMANCE DETAILS

PROPERTIES

Specific Gravity (ASTM D792)	1.3	
Tensile Strength (ASTM D638)	6,000 psi	41 MPa
Modulus of Elasticity (ASTM D638)	3.0 x 10 ⁵ psi	2,068 MPa
Flexural Strength (ASTM D790)	9,200 psi	63.4 MPa
Flexural Modulus (ASTM D790)	3.5 x 10 ⁵ psi	2,413 MPa
Hardness Rockwell R (ASTM D785)	105	
Hardness Shore D (ASTM D2240)	80	
Compression Strength (ASTM D695)	7,400 psi	51 MPa
Shear Strength (ASTM D732)	5,300 psi	36.5 MPa
Water Absorption (ASTM D570)	0.05%/24H	
Izod Impact Notched (ASTM D256)	73 °F 10-15 ft-lb/in	23 °C 534-801 J/m

*Independent lab tests at 73°F (22.8°C) in dry conditions unless otherwise noted.

SHEET SIZES

Lengths	to 96 in	2,438 mm
Widths	to 48 in	1,219 mm
Gauges	0.062 in to 1 in	1.57 mm to 25.4 mm
Custom	Blank sizes, gauges on request	

ELECTRICAL

Dielectric Strength (ASTM D149)	350 Volts/Mil.
Volume Resistivity (ASTM D257)	5.26 x 10 ⁻¹⁴ Ohms/cm
Dielectric Constant (ASTM D150)	4.00 @60Hz
Dissipation Factor (ASTM D150)	0.005 @60Hz
Loss Index (ASTM D150)	0.02

THERMAL

Thermal Expansion (ASTM D696)	2.50 x10 ⁻⁵ °F	4.50 x10 ⁻⁵ °C
Heat Deflection Annealed (ASTM D648)	150 °F @ 264 psi	66 °C @ 1.8 MPa
Thermal Conductivity (ASTM C177)	0.50 BTU/HR/FT/F/in.	
Specific Heat (ASTM C351)	0.29 CAL/GM/°C	

FLAMMABILITY

UL 94	V-0
-------	-----

*Values based on a minimum thickness of 1.5 mm (.059 inches), UL File #: E54688

4300
CLEAR TYPE II PVC

DESIGN OPTIONS

- Color** Clear with a "blue" tint
- Textures** Smooth polished surface (both sides)
- Masking** Standard (both sides)



www.boltaron.com | +1 800 342 7444

RELIABILITY MEETS INNOVATION

DISCLAIMER AND LIMITATION OF WARRANTY: All information contained herein is believed by SIMONA BOLTARON Inc. to be reliable. Typical properties are based on laboratory tests conducted on material samples in accordance with standard test methodology. SIMONA BOLTARON Inc. makes no express or implied warranty that its products will perform in accordance with the data in all conditions and circumstances. To determine suitability for use, users must test applications under actual operating conditions. As a result, ALL EXPRESS OR IMPLIED WARRANTIES IN CONNECTION WITH SIMONA BOLTARON Inc. PRODUCTS INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY DISCLAIMED. RI 1.31.23