

Rigiwall® 4333

HIGH IMPACT SHEET

Boltaron Rigiwall® 4333 is a proprietary, UL Standard 723 listed, calendared Acrylic/PVC Alloy sheet, designed as a durable, protective, interior wall covering. Boltaron Rigiwall® 4333 offers a class 1/A building code rating, excellent impact strength, abrasion resistance, and stain and chemical resistance.

CHARACTERISTICS

- Impact resistance
- Damage resistant
- Low minimums
- Thermoformable

USES

- Interior wall covering

PERFORMANCE DETAILS

PROPERTIES

Specific Gravity (ASTM D792)	1.37	
Tensile Strength (ASTM D638)	5,200 psi	36 MPa
Flexural Strength (ASTM D790)	8,300 psi	57 MPa
Flexural Modulus (ASTM D790)	290,000 psi	2,000 MPa
Hardness Rockwell (ASTM D785)	106	
Izod Impact Notched (ASTM D256)	73 °F 10-15ft-lb/in	23 °C 534-801 J/m
Heat Deflection Annealed (ASTM D648)	165 °F @264 psi	73.9 °C @1.82 MPa
Taber Abrasion Wt Loss CS17 Wheel (ASTM D3389-15) 1 kg, 1000 cycles	0.073 mg/rev	
Thermal Expansion (ASTM D696)	5.0 x10 ⁻⁵ °F	9.0 x10 ⁻⁵ °C
Dimensional Stability 5' x 320°F	13%	
Dimensional Stability 24 hrs @ 158°F	1%	
Dimensional Stability 7 days @ 158°F	1%	
PRO BW (ASTM E96)	0.13 US perms	
PRO B (ASTM E96)	0.08 US perms	
Color change in L*a*b* units 24 hrs @ 158°F	0.04	
Color change in L*a*b* units 7 days @ 158°F	0.06	

*Independent lab tests at 73°F (22.8°C) in dry conditions unless otherwise noted.

SHEET SIZES

Lengths	to 120 in	3,048 mm
Widths	to 60 in	1,524 mm
Gauges	from 0.018	0.475 mm continuous rolls available
Thickness	0.040 in	1.106 mm
Custom	Blank sizes, gauges on request	

FLAMMABILITY

	Flame Spread	Smoke Developed
@0.025 in max. (ASTM E84)	10	30
@0.029 in max. (ASTM E84)	15	15
@0.043 in max. (ASTM E84)	15	60
@0.064 in max. (ASTM E84)	15	200
Class 1-A requirements (ASTM E84)	<25	<450

BUILDING
& RETAIL

4333
HIGH IMPACT

DESIGN OPTIONS

- Colors** Unlimited
- Textures** Wide range available
- Minimum** 500 lb

SIMONA
boltaron

www.boltaron.com | +1 800 342 7444

RELIABILITY MEETS INNOVATION

DISCLAIMER AND LIMITATION OF WARRANTY: All information contained herein is believed by SIMONA BOLTARON Inc. to be reliable. Typical properties are based on laboratory tests conducted on material samples in accordance with standard test methodology. SIMONA BOLTARON Inc. makes no express or implied warranty that its products will perform in accordance with the data in all conditions and circumstances. To determine suitability for use, users must test applications under actual operating conditions. As a result, ALL EXPRESS OR IMPLIED WARRANTIES IN CONNECTION WITH SIMONA BOLTARON Inc. PRODUCTS INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY DISCLAIMED. RI 3.5.20