Boltaron® 4225

FM 4910 CPVC

CHARACTERISTICS

- Meets FM 4910
- Suitable for thermoforming
- Smooth, polished surface

USES

- Semiconductor cleanroom parts
- Machined parts
- Thermoformed parts

PERFORMANCE DETAILS

PROPERTIES

Specific Gravity (ASTM D792)	1.4	462	
Tensile Strength (ASTM D638)	7,360 psi	51 MPa	
Modulus of Elasticity (ASTM D638)	3.9 x 10⁵ psi	2,689 MPa	
Flexural Strength (ASTM D790)	12,000 psi	83 MPa	
Flexural Modulus (ASTM D790)	3.8 x 10 ⁵ psi	2,620 MPa	
Hardness Rockwell R (ASTM D785)	11	117	
Compression Strength (ASTM D695)	10,544 psi	73 MPa	
Compression Modulus (ASTM D732)	3.28 x10 ⁵ psi	2,261 MPa	
Water Absorption 24 hrs. (ASTM D570)	0.0	0.07%	
Izod Impact Notched (ASTM D256)	73 °F > 2 ft-lb/in	23 °C > 107 J/m	

^{*}Independent lab tests at 73°F (22.8°C) in dry conditions unless otherwise noted.

ELECTRICAL

Dielectric Strength (ASTM D149)	1,518 Volts/Mil.
Dielectric Constant (ASTM D150) 10 KHz 100 KHz 1 MHz	2.973 2.913 2.845
Dissipation Factor (ASTM D150)	
10 KHz 100 KHz 1 MHz	0.012 0.015 0.017

THERMAL

Thermal Expansion (ASTM D696)	6.3 x10 ⁻⁵ °F	1.10 x10 ⁻⁴ °C
Heat Deflection Annealed (ASTM D648)	205 °F @ 264 psi	

FLAMMABILITY

FM Global (FM 4910)	Approved

SHEET SIZES

311221 31223		
Lengths	to 96 in	2,438 mm
Widths	to 48 in	1,219 mm
Gauges	0.250 in to 1 in	6.35 mm to 25.4 mm
Custom Blank sizes, gauges on request		

Attention: Avoid using cleaners containing quaternary ammonium compounds. In some cases, disinfectants containing quaternary ammonium compounds (QACs) could cause discoloration when left on at elevated temperatures and should be avoided for use on this grade of Boltaron material. For a full cleaning guide, visit www.boltaron.com/cleaning-and-disinfecting.

DISCLAIMER AND LIMITATION OF WARRANTY: All information contained herein is believed by SIMONA BOLTARON Inc. to be reliable. Typical properties are based on laboratory tests conducted on material samples in accordance with standard test methodology, SIMONA BOLTARON Inc. makes no express or implied warranty that its products will perform in accordance with the data in all conditions and circumstances. To determine suitability for use, users must test applications under cartual operating conditions. As a result, ALL EXPRESS OR IMPLIED WARRANTIES IN CONNECTION WITH SIMONA BOLTARON Inc. PRODUCTS INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY DISCLAIMED. RI 5.17.21

CORROSION

RESISTANT



DESIGN OPTIONS

Color Bright white
Texture Smooth polis

Smooth polished surface (both sides)

Masking Standard (both sides)

