

Boltaron® 9250/9250C

FAR RATED HIGH TEMPERATURE-RESISTANT LIGHT BLOCKING SHEET

9 0 0 0
S E R I E S

Boltaron® 9250/9250C are proprietary, thin gauge thermoplastic sheet products that combine maximum light-blocking characteristics with high temperature resistance for aircraft window shades. 9250 is a single color sheet, and 9250C features a double color construction. They offer durability and uniform thermoforming characteristics, and resist abrasion, stains and many chemicals. Both also meet stringent FAR flammability criteria.

CHARACTERISTICS

- Maximum light-blocking in thin gauges
- Meets FAR flame test criteria
- Single and double color construction

USES

- Aircraft window shades

PERFORMANCE DETAILS

FAR RATINGS

FAR 25.853(a)(i)	(Flammability) (Vertical burn, 60 sec) Pass
FAR 25.853(a)(ii)	(Flammability) (Vertical burn, 12 sec) Pass

PROPERTIES

Specific Gravity (ASTM D792)	1.47	
Tensile Strength (ASTM D638)	7,400 psi	51 MPa
Flexural Strength (ASTM D790)	11,000 psi	75.9 MPa
Flexural Modulus (ASTM D790)	380,000 psi	2,620 MPa
Izod Impact Notched (ASTM D256)	73 °F 2.0 ft-lb/in	23 °C 106.8J/m
Hardness Rockwell (ASTM D785)	119	
Heat Deflection Annealed (ASTM D648)	200-205 °F @264 psi	93-96 °C @1.8 MPa
Thermal Expansion (ASTM D696)	1.67x10 ⁻⁵ /°F	3x10 ⁻⁵ /°C

* Independent lab tests. All tests at 73 °F (23 °C) in dry conditions unless otherwise noted.

SHEET SIZES

Lengths	to 120 in	3,048 mm
Widths	to 48 in	1,220 mm
Gauges	from 0.047 to 0.060 in	from 1.02 to 1.52 mm

Custom Blank sizes, gauges on request

THERMOFORMING GUIDELINES

Forming Temperature	380-420 °F (193-215°C)
----------------------------	------------------------

9250
LIGHT BLOCKING

DESIGN OPTIONS

Colors Unlimited
Textures Wide range available

Attention: Use caution when using cleaners containing quaternary ammonium compounds. Follow all label instructions and remove cleaner residues completely after cleaning. Avoid using quaternary ammonium compounds on parts exposed to elevated temperatures. For a full cleaning guide, visit www.boltaron.com/cleaning-and-disinfecting.

DISCLAIMER AND LIMITATION OF WARRANTY: All information contained herein is believed by SIMONA BOLTARON Inc. to be reliable. Typical properties are based on laboratory tests conducted on material samples in accordance with standard test methodology. SIMONA BOLTARON Inc. makes no express or implied warranty that its products will perform in accordance with the data in all conditions and circumstances. To determine suitability for use, users must test applications under actual operating conditions. As a result, ALL EXPRESS OR IMPLIED WARRANTIES IN CONNECTION WITH SIMONA BOLTARON Inc. PRODUCTS INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY DISCLAIMED. RI 8.14.24

SIMONA
boltaron

www.boltaron.com | +1 800 342 7444

RELIABILITY MEETS INNOVATION