

# Boltaron® 9815 Film

THERMOFORMABLE FAR-RATED SHEET WITH FILM

9 0 0 0  
S E R I E S

## CHARACTERISTICS

- Can be laminated to flat or three-dimensional metal, FRP or thermoplastic substrates
- Uniform high quality appearance
- Full color range
- Lot-to-lot color consistency

## USES

- Class dividers and bulkhead laminates
- Galley and lavatory components
- Bull noses, gap covers and moldings
- Light housings, video monitor shrouds
- passenger service units (PSUs)

## PERFORMANCE DETAILS

### FAR RATINGS

FAR 25.853(a)(i)	(Flammability) (Vertical burn, 60 sec) Pass
FAR 25.853(a)(ii)	(Flammability) (Vertical burn, 12 sec) Pass
FAR 25.853(d)(Part IV)	(OSU Heat Release) (Peak - HRR, kW/m <sup>2</sup> <65) (2 Min - HRR, kW min/m <sup>2</sup> <65)
FAR 25.853(d)(Part V)	(NBS Smoke) (Ds Max <200)

### PROPERTIES

<b>Specific Gravity</b> (ASTM D792)	1.49	
<b>Tensile Strength @ yield</b> (ASTM D638)	5,500 psi	38 MPa
<b>Flexural Strength</b> (ASTM D790)	8,700 psi	60 MPa
<b>Flexural Modulus @ yield</b> (ASTM D790)	410,000 psi	2,827 MPa
<b>Izod Impact Notched</b> (ASTM D256)	73 °F 5.0 ft-lb/in	23 °C 265 J/m
<b>Rockwell Hardness R-scale</b> (ASTM D785)	107	
<b>Heat Deflection Annealed</b> (ASTM D648)	170 °F @264 psi	77 °C @1.8 MPa
<b>Thermal Expansion</b> (ASTM D696)	1.67 x 10 <sup>-5</sup> /°F	3 x 10 <sup>-5</sup> /°C

\* Independent lab tests. All tests at 73 °F (23 °C) in dry conditions unless otherwise noted.

### SHEET SIZES

<b>Lengths</b>	to 120 in	3,048 mm
<b>Widths</b>	to 60 in	1,524 mm
<b>Gauges</b>	from 0.010 to 0.40 in	from 0.25 to 1.02 mm
<b>Rolls</b>	Available on request in gauges	≤ 0.040 in 1.02 mm
<b>Custom</b>	Blank sizes, gauges on request	

9815

### DESIGN OPTIONS

**Colors** Unlimited  
**Textures** Matte/Matte  
Complements 9815E  
Coarse Matte (CM)

**Attention:** Use caution when using cleaners containing quaternary ammonium compounds. Follow all label instructions and remove cleaner residues completely after cleaning. Avoid using quaternary ammonium compounds on parts exposed to elevated temperatures. For a full cleaning guide, visit [www.boltaron.com/cleaning-and-disinfecting](http://www.boltaron.com/cleaning-and-disinfecting).

DISCLAIMER AND LIMITATION OF WARRANTY: All information contained herein is believed by SIMONA BOLTARON Inc. to be reliable. Typical properties are based on laboratory tests conducted on material samples in accordance with standard test methodology. SIMONA BOLTARON Inc. makes no express or implied warranty that its products will perform in accordance with the data in all conditions and circumstances. To determine suitability for use, users must test applications under actual operating conditions. As a result, ALL EXPRESS OR IMPLIED WARRANTIES IN CONNECTION WITH SIMONA BOLTARON Inc. PRODUCTS INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY DISCLAIMED. RI 1.20.26

**SIMONA**  
**boltaron**

[www.boltaron.com](http://www.boltaron.com) | +1 800 342 7444

RELIABILITY MEETS INNOVATION