

Boltaron® 9815 with an Extruded Texture

FAR RATED HIGH IMPACT SHEET FOR AIRCRAFT INTERIORS

9 0 0 0
S E R I E S

CHARACTERISTICS

- Outstanding impact resistance
- Uniform high quality appearance
- Wall thickness integrity in deep draw forming
- Full range of colors, finishes
- Lot-to-lot color consistency

USES

- Instrument panel housings and air ducts
- Class dividers and bulkhead laminates
- Galley and lavatory components
- Bull noses, gap covers and moldings
- Aircraft seating components

PERFORMANCE DETAILS

FAR RATINGS

FAR 25.853(a)(i)	(Flammability) (Vertical burn, 60 sec) Pass
FAR 25.853(a)(ii)	(Flammability) (Vertical burn, 12 sec) Pass
FAR 25.853(d)(Part IV)	(OSU Heat Release) (Peak - HRR, kW/m² <65) (2 Min - HRR, kW min/m² <65)
FAR 25.853(d)(Part V)	(NBS Smoke) (Ds Max <200)

PROPERTIES

Specific Gravity (ASTM D792)	1.49	
Tensile Strength @ yield (ASTM D638)	5,500 psi	38 MPa
Flexural Strength (ASTM D790)	8,700 psi	60 MPa
Flexural Modulus @ yield (ASTM D790)	410,000 psi	2,827 MPa
Heat Deflection Annealed (ASTM D648)	170 °F @264 psi	77 °C @1.8 MPa
Thermal Expansion (ASTM E831)	3.8 x 10 ⁻⁵ /°F	6.9 x 10 ⁻⁵ /°C

* Independent lab tests. All tests at 73 °F (23 °C) in dry conditions unless otherwise noted.

SHEET SIZES

Lengths	to 120 in	3,048 mm
Widths	to 60 in	1,524 mm
Gauges	from 0.040 to 0.250 in	from 1.02 to 6.35 mm
Custom Blank sizes, gauges on request		

THERMOFORMING PARAMETERS

Forming Temperature	335 - 370°F	168 - 188°C
Typical Heater Settings	30 - 50% Top 50 - 70% Bottom	
Drying	Not required	



DESIGN OPTIONS

Colors	Unlimited
Textures	Wide Range Available
Effects	True Pearl
Images	Impress Printing®

Attention: Use caution when using cleaners containing quaternary ammonium compounds. Follow all label instructions and remove cleaner residues completely after cleaning. Avoid using quaternary ammonium compounds on parts exposed to elevated temperatures. For a full cleaning guide, visit www.boltaron.com/cleaning-and-disinfecting.

DISCLAIMER AND LIMITATION OF WARRANTY: All information contained herein is believed by SIMONA BOLTARON Inc. to be reliable. Typical properties are based on laboratory tests conducted on material samples in accordance with standard test methodology. SIMONA BOLTARON Inc. makes no express or implied warranty that its products will perform in accordance with the data in all conditions and circumstances. To determine suitability for use, users must test applications under actual operating conditions. As a result, ALL EXPRESS OR IMPLIED WARRANTIES IN CONNECTION WITH SIMONA BOLTARON Inc. PRODUCTS INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY DISCLAIMED. RI 8.17.26



www.boltaron.com | +1 800 342 7444

RELIABILITY MEETS INNOVATION